

Refractory Cement MB50-5

General description

This product is a super duty air set mortar supplied ready for use. It is a volume stable, highly refractory mortar. It shows no sign of flowing from pier testing joints at 1600°C.

HEALTH AND SAFETY PRECAUTIONS

The binders in this material are of an alkaline nature and care should be exercised whilst handling. Protective eye and hand equipment must be worn. In case of contact with bare skin, promptly remove by thoroughly washing with clean water.

Application Data

Maximum Service Temperature (deg C) 1600

Application:

Amount to lay 1000 bricks
230 x 115 x 75mm straits =
210 Kgs

Installation Method Hand trowel

TYPICAL CHEMICAL ANALYSIS (%)

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	CaO	TiO	MgO	Alkalies
43	43	.8	0.1	1.2	0.1	3.3

Shelf Life:

6 months

Form:

SB50

Revision No:

0

Authorised:

Pp

Issue Date:

1/17/2007

Date Packed

Furnace Technologies Pty Ltd abn: 47 063 407 581 , 15 Weatherburn way Kardinya 6153

Phone 61 (8) 9314 6858 Fax 61(8) 9314 1251

<http://www.furnace-technologies.com.au>

tech@furnace-technologies.com.au

Size

5 Kg