



Cast Panel Cement

General description	A trowel grade , low iron refractory cement.
Recommend use	Based on premium grade raw materials and binders, this product is developed for the use as a repair material for furnaces operating at high temperatures. It has a maximum service temperature of 1600°C.
Application	Apply in thin joints.
Shelf Life	Six Months Storage of the product should be in a cool, dry place.
HEALTH AND SAFETY PRECAUTIONS	No health hazards associated with normal use. May be abrasive and alkaline to delicate skin. Requires no special storage. Spillages may be cleaned by any convenient method.

Typical Chemical Analysis (%)

AL ₂ O ₃	SiO ₂	FE ₂ O ₃	Calcined Bauxite
5—10%	15—25%	0	70—80%