



GENERAL DESCRIPTION	A trowel grade, low iron refractory castable based on premium grade raw materials and binders. This product is developed for use as repair material for furnaces and ladles operating at high temperature	
TYPICAL CHARACTERISTICS	Max service temp	1600°C
	Application	Hand trowel and pack
	Cast SG	2.375–2.425
	Water Addition	12–15%
RECOMMEND USE	Used as a grout for patching refractory bricks and linings.	
SHELF LIFE	Six Months Storage of the product should be in a cool, dry place.	
HEALTH AND SAFETY PRECAUTIONS	No health hazards associated, in normal use. It may be slightly abrasive and alkaline to a delicate skin. It requires no special storage. Small spillages may be cleaned by any convenient method. Use standard dust and skin protection.	

TYPICAL CHEMICAL ANALYSIS (%)						
Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	CaO	SiC	ZrO ₂	Alkali
85	7.5	1	4.05	---	---	0.2

CONTACT US

P: +61 8 9417 4226 | F: +61 8 9417 9827

E-Mail: sales@furnace-technologies.com.au

www.furnace-technologies.com.au

Furnace Technologies Pty Ltd

60 Cutler Road, Jandakot, WA 6164